



Anti-slip paper products with a proven technology

Tests	Units	Median Value	Tolerances	References
Grammage	g / m ²	550	+/- 10%	ISO 536
Thickness	µm	865	+/- 10%	ISO 534
Burst Index	kPa	1050	Indicatives values	ISO 2758
Stiffness TABER (MD) (CD)	g.cm	810 320	Indicatives values	ISO 2493
Tensile Strength (MD) (CD)	kN.m	4870 1930	Indicatives values	//
Coefficient of friction			>0.60	

Test and certify by VDZ GmbH laboratory with dynamic friction coefficient $\mu > 0,6$ (specification VDI 2700 part. 14)

- ✓ Easy and simple handling
- ✓ Available in all sizes required
- ✓ 100 % recyclable environment-friendly basic material paperboard
- ✓ Special coating for a reliable load securing.
- ✓ Cost saving material

TECHNICAL DATA
STABILIZATOR
550 gsm